

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan


“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 6899 (1997): Textiles - High density polyethylene (HDPE) woven fabrics [TXD 23: Textile Materials made from Polyolefins]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



n

IS 6899 : 1997

भारतीय मानक

वस्त्रादि — उच्च घनत्व वाले पोलिइथाइलीन (एच. डी. पी. ई.)

के बुने कपड़े — विशिष्ट

(दूसरा पुनरीक्षण)

Indian Standard

TEXTILES — HIGH DENSITY
POLYETHYLENE (HDPE) WOVEN
FABRICS — SPECIFICATION

(Second Revision)

ICS 59.080.30

© BIS 1997

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

September 1997

Price Group 1

FOREWORD

This Indian Standard (Second Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Textile Materials Made from Polyolefins (Excluding Cordage) Sectional Committee had been approved by the Textile Division Council.

This standard originally published in 1973 was revised in 1984.

The standard has been revised again to modify the mass and breaking load of the various varieties of HDPE fabric in view of the availability of HDPE tapes of superior tensile properties. Provision has been made for supply of fabric having mass other than those specified in the standard subject to agreement between the buyer and the seller.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value observed or calculated, expressing the result of a test shall be rounded off in accordance with IS 2 : 1960 'Rules for rounding off numerical values (*revised*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard

TEXTILES — HIGH DENSITY POLYETHYLENE (HDPE) WOVEN FABRICS — SPECIFICATION

(Second Revision)

1 SCOPE

This standard specifies requirements of five varieties of high density polyethylene (HDPE) woven fabrics generally used for wrapping, bale covering and similar applications.

2 REFERENCES

The following Indian Standards are necessary adjuncts to this standard :

IS No.	Title
1954 : 1990	Determination of length and width of woven fabrics — Methods (<i>second revision</i>)
1964 : 1970	Methods for determination of weight per square metre and weight per linear metre of fabrics (<i>first revision</i>)
1969 : 1985	Methods for determination of breaking load and elongation of woven textile fabrics (<i>second revision</i>)
4905 : 1968	Method for random sampling
6192 : 1994	Textiles — Monoaxially oriented high density polyethylene tapes — Specification (<i>second revision</i>)

3 MANUFACTURE

3.1 The fabric shall be woven in plain weave from monoaxially oriented HDPE tapes conforming to IS 6192.

3.1.1 HDPE tapes used for manufacturing the fabric for prolonged outdoor application shall be resistant to ultra-violet radiation. This shall be achieved by using a suitable percentage of carbon black in the HDPE granules or by using ultra-violet stabilized grade of HDPE granules as specified in the contract or order.

3.2 The fabric shall have uniform and straight selvages and shall be free from weaving defects, such as holes, cuts, tears, oil stains, etc.

4 REQUIREMENTS

4.1 The high density polyethylene (HDPE) woven fabric shall conform to the requirements given in Table 1.

4.1.1 Fabrics of mass other than those given in Table 1 may also be used subject to agreement between the buyer and the seller. In such case the fabric shall conform to breaking load calculated as under. For calculation of breaking load, tenacity of the HDPE tape shall be taken as 4.0 g/d, minimum.

NOTE — The strength may be calculated by the following formula:

$$\text{a) Strength/5 cm width} = 4.0 \times \frac{D}{1\,000} \times \frac{M}{2} \text{ or } \frac{N}{2} \times 9.81 \text{ Newtons}$$

where

D = Denier of the tape,

M = Warp/dm, and

N = Weft/dm.

Table 1 Requirements of HDPE Fabrics
(Clauses 4.1 and 4.1.1)

Variety No.	Mass of Unlaminated Fabric, g/m ² Min	Breaking Load on 5.0 cm × 20 cm Cut Strips, N, Min		Width	Length
		Warpway	Weftway		
(1)	(2)	(3)	(4)	(5)	(6)
1	53	410	350	As agreed to between the buyer and the seller	As agreed to between the buyer and the seller
2	70	540	465		
3	89	680	590		
4	110	755	650		
5	130	1 000	860		
Tolerance	—	—	—	± 2.0 percent	—
Method of Test	IS 1969	IS 1969		IS 1954	

NOTE — In case of laminated fabric, the increase in mass due to lamination of the fabric shall be at least 23 g/m².

5 PACKING

A suitable length of the fabric shall be formed into a roll. Each roll of the fabric shall be packed in a layer of HDPE film or as agreed to between the buyer and the seller.

6 MARKING

6.1 Each roll of the fabric shall be marked with the following information:

- a) Name of the material;
- b) Length (m) and width (cm) of the fabric;
- c) Indication of the source of manufacture; and
- d) Year of manufacture.

6.1.1 BIS Certification Marking

The roll may also be marked with the Standard Mark.

6.1.2 The use of the Standard Mark is governed by the provisions of the *Bureau of Indian Standards Act, 1986* and the rules and regulations made thereunder. The details of the conditions under which the licence for the use of Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

7 SAMPLING AND CRITERIA FOR CONFORMITY

7.1 Lot

In any consignment all the rolls of fabric of same construction shall be grouped together to constitute a lot.

7.2 The number of rolls of fabric to be selected from a lot shall be in accordance with Table 2. The rolls shall be selected at random with the use of random number tables (*see* IS 4905).

7.3 The conformity of the lot to the requirements of this standard shall be determined on the basis of the tests on the samples selected from it.

7.4 Tests and Criteria for Conformity

Fabric from each roll selected from the lot shall be tested for length, width, mass and breaking load. Any roll failing to meet the requirements as specified in Table 1 shall be considered a defective. The lot shall be considered acceptable, if the number of defective rolls does not exceed the permissible number given in col 3 of Table 2.

Table 2 Scale of Sampling and Criteria for Conformity
(Clauses 7.2 and 7.4)

No. of Rolls of Fabric in the Lot	No. of Rolls of Fabric to be Selected	Permissible No. of Defects
(1)	(2)	(3)
Up to 50	5	0
51 to 100	8	0
101 to 300	13	1
301 and above	20	1

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 1986* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Handbook' and 'Standards: Monthly Additions'.

This Indian Standard has been developed from Doc : No. TX 23 (0069).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002
Telephones : 323 01 31, 323 33 75, 323 94 02

Telegrams : Manaksanstha
(Common to all offices)

Regional Offices :

Telephone

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg
NEW DELHI 110002

{ 323 76 17
323 38 41

Eastern : 1/14 C. I.T. Scheme VII M, V. I. P. Road, Maniktola
CALCUTTA 700054

{ 337 84 99, 337 85 61
337 86 26, 337 91 20

Northern : SCO 335-336, Sector 34-A, CHANDIGARH 160022

{ 60 38 43
60 20 25

Southern : C. I. T. Campus, IV Cross Road, CHENNAI 600113

{ 235 02 16, 235 04 42
235 15 19, 235 23 15

Western : Manakalaya, E9 MIDC, Marol, Andheri (East)
MUMBAI 400093

{ 832 92 95, 832 78 58
832 78 91, 832 78 92

Branches : AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR. COIMBATORE.
FARIDABAD. GHAZIABAD. GUWAHATI. HYDERABAD. JAIPUR. KANPUR.
LUCKNOW. NAGPUR. PATNA. PUNE. THIRUVANANTHAPURAM.